

TERMIX

POLVERI DI COPERTURA PER MATEROZZE HOT TOPPING COMPOUNDS

TIPI STANDARD STANDARD TYPES	TERMIX AC 303	TERMIX AC 304	TERMIX B/A
Isolante <i>Insulating</i>	X	X	
Espandibile <i>Expansible</i>	X	X	
Esotermica lenta <i>Slow exothermic</i>		X	
Esotermica media <i>Medium exothermic</i>	X		
Esotermica veloce <i>Speed exothermic</i>			X
Inizio reazione <i>Start of reaction</i>	>4'	>5'	5"
Fine reazione <i>End of reaction</i>	>10'	>15'	>1' <2'
ANALISI CHIMICA CHEMICAL ANALYSIS	TERMIX AC 303	TERMIX AC 304	TERMIX B/A
Al met	20-25%	14-20%	14%
SiO ₂	13-20%	17-23%	4-5%
Al ₂ O ₃	40-45%	35-45%	0,5-1%
CaO+MgO	0,01-0,1%	0,01-0,1%	—
Na ₂ O+K ₂ O	1-3%	1-3%	—
Fe ₂ O ₃	0,1-1%	0,1-1%	—
Fe	—	—	68-69%
F ⁻	0,01-1%	0,01-1%	1,5-2%
C tot	7-10%	4-7%	—
Peso specifico <i>Specific weight</i>	0,60-0,70 g/cm ³	0,50-0,60 g/cm ³	1,5-1,6 g/cm ³

Altri tipi disponibili su richiesta del cliente. - Other types available from customer's request.